

Designed for possibilities.

Made for people.

Ground



# Altro Whiterock<sup>™</sup> Matte product datasheet

Textured wall protection for busy spaces.

# **Altro Whiterock Matte**

Doors and plasterboard walls can easily be damaged, be it scrapes and knocks as people pass, or more serious dents and holes caused by wheeled traffic. Altro Whiterock Matte has been specifically designed to protect these surfaces. Altro Whiterock Matte is dense, impervious and resistant to bumps. It features a lightly-textured surface, which camouflages scuffs, keeping the wall area looking better for longer.

Available in five colors, Altro Whiterock Matte matches many Altro Whiterock shades. This offers flexibility with design, making it a versatile solution across a range of areas. The color runs throughout, reducing the visibility of knocks or scrapes.

With an impervious, easy-to-wipe surface, Altro Whiterock Matte improves cleanability, which is a major advantage within its recommended application areas.

## Typical applications

High-traffic areas, corridors, food manufacturing, back-of-house

#### Features + benefits

- Lightly-textured surface
- Impact-resistant
- Camouflages damage caused by wheeled traffic
- Easy to clean
- Impervious, integrated floor and wall system
- Low VOCs
- ICC-ES Product Certified

#### Complete flexibility

The Altro walls system was introduced over 35 years ago and has been a market leader ever since. Providing creative freedom to designers, specifiers and end users, our effective, impervious panels deliver a safe, decorative and hygienic wall solution that meets aesthetic and performance requirements with a variety of shades and textures.

Designed to seamlessly integrate with Altro flooring, our wall cladding ranges offer complete design flexibility for any environment.

- · Heat formable on site
- Reduced cleaning and maintenance costs
- Extremely hygienic
- Impervious to water ingress
- Exceptional long-term durability and impact resistance
- Phthalate and biocide-free

### Better together

Altro wall cladding coordinates exceptionally well with our safety, slip-resistant and smooth flooring ranges, allowing an extensive suite of creative options all under the Altro name.













Pearl 10' / 3.0m W151/FT41

LRV 83 WSR 41 A805/41

Almond 10' / 3.0m W151/FT32

LRV 70 WSR 32 A805/32

Battleship 10' / 3.0m W151/FT208

LRV 43 WSR 208 A805/208 Tan 10' / 3.0m W151/FT206


LRV 41 WSR 206 A805/206

Denim 10' / 3.0m W151/FT201

LRV 32 WSR 201 A805/201



Color matched weldrod (WSR) and sanitary sealant (A805) is available. You'll find their product codes under product LRVs.








Thickness	2.5mm   .10"			USDA	Altro Whiterock is USDA compliant	
Dimensions	10' - 4' x 9' 10"   1.22m x 3.0m			Altro Whiterock is FDA compliant		
Weight	10' panel - 28.22 lbs   12.8 kg			USP	Altro Whiterock conforms to the hygienic standards of USP 797	
Warranty	20 year product warranty	20 years		CFIA	Altro Whiterock is CFIA compliant	
Life expectancy	30 year If expectancy	30 years		CENTIFICATION	HACCP International certified	
Fire and smoke performance	CAN/ULC-S102.1 CAN/ULC-S102.2 ASTM E84-18	Tested Tested Class A		Density (g/cm3)	ISO 1183	1.39
Impact Resistance	ASTM D5420	Up to 198 inch lbs in force		Flexural strength (Mpa)	ISO 178	79.8
VOC emissions	CA 01350	Pass		Shore hardness, Type D	ISO 868	79
Particle concentration	ISO 14644-1:12	Meets ISO Class 2 cleanroom		Volume resistance RD (Ω)	DIN IEC 60 093	6.90E+13
Max service temperature	140°F (60°C)			Dielectric constant	DIN 53483	3.2
Tensile strength (Mpa)	ISO 527	48		Thermal conductivity - "K Value" (W/mK)	DIN 52612	0.16
Surface resistance ROE (Ω)	DIN IEC 60 167	2.00E +14		Coefficient of linear thermal expansion	DIN 53752	7.10-5 at 68°F (20°C) after 1 hr storage at 194°F (90°C) (104/K)
Dielectric strength (KV/mm)	DIN IEC 243	16.8		Vicat softening point VST/B	ISO 306	176°F (80°C)
Dielectric loss index	DIN 53483	0.02		Heat distortion temperature	ISO 75-2	140°F (60°C)
"U Value" bonded to 100mm block wall (W/ m² °C)	DIN 52612	1.8		Water absorption	ISO 62	24 hrs030% 168 hrs093% 216 hours106%
Compressive strength (N/mm²)	DIN 53454	70		F	Fungi resistance ASTM G21	Passes rating 0* *achieves zero growth after 21 days
Water absorption	ISO 62	24 hrs030% 168 hrs093% 216 hours106%		UV exposure	ASTM G154	Tested
	Mold resistance ASTM D3273	Excellent Score of 10		ËS	ANSI/ICPA SS-1 2001 IAPMO PS 106-2015e1	Certified
Composition	Extruded semi-rigid virgin PVCu with a tight molecular structure and incorporated UV stabilizers.					
Installation	Must be installed by a professional installer that has attended the Altro Whiterock Installation Clinic as part of the Altro Whiterock Elite Partner program. Installation procedures must follow the instructions detailed in the Altro Whiterock Installation Guide. Failure to install using the complete Altro Whiterock System could void the limited product warranty.					

Altro and Altro Whiterock are trademarks of Altro Limited. Book content was correct at time of print. Altro reserves the right to change any detail. Please consult your sales representative for the latest product information.

© Copyright Altro USA 2024



Discover more of our sustainability story and credentials at altro.com







Order samples 24 hours a day at altro.com and materialbank.com

#### Discover more online!









Maintenance guide

Warranty form

Literature

LEED form

#### Even more great resources!

- BIM components
- SDS sheets
- Detail drawings and CAD files
- High-resolution swatch downloads
- Photo galleries www.altropics.com
- Solutions by area type ORs, labs and cleanrooms, kitchens, senior living and more!

Follow us



- **USA** 800 377 5597
- **♥ CANADA** 800 565 4658
- support@altro.com
- www.altro.com

Content was correct at time of print. Altro reserves the right to change any detail. Please consult www.altro.com or your local Sales Representative for the latest product information