



# altro

## EcoFix™ 65 Spray

This spray adhesive may be used with Altro Lavencia Plus, Altro Quartz Tile, Altro Dolce and Altro Dolce Essentials

Coverage: 150 - 185 ft<sup>2</sup> (14 - 17.2 m<sup>2</sup>)

5 year warranty

Warranted for: 8lbs MVER, 95% RH, 11pH

### Product characteristics

Versatile spray adhesive naturally suited for adhering tile and/or plank products in commercial and residential applications.

Uses 80% less adhesive compared to trowel-applied epoxy and bucket adhesive. Ecofix 65's instant shear strength allows for all traffic without any adhesive indentation, displacement, or movement associated with heavy weight-bearing loads.

Non-toxic, 0.020 g/ml VOC product that allows occupation of space as soon as installation is complete.

### Coverage guide

LVT, LVP, Tile - Upside down aerosol  
150-185 sq ft

### Advantages

- Uses 80% less adhesive
- Allows for all traffic immediately
- 0.020 g/ml VOC content
- Non-toxic, water-based adhesive
- No need to shut down HVAC
- Easy water cleanup while adhesive is still wet
- Non-flammable
- High moisture and pH resistant
- No offensive odors
- FloorScore certified

### Suitable substrates

Bonds Altro Lavencia to the following properly prepared, smooth, flat, dust-free substrates:

- Concrete
- Underlayment grade plywood
- Metal
- Fiberglass
- Existing VCT



### LEED facts

LEED v4

This product may help contribute to the following credits

EcoFix 65 Spray

1



Environmental quality  
Low emitting materials, adhesives

1

Discover more of our sustainability story and credentials at [altro.com/sustainability](http://altro.com/sustainability)

### Technical data

Chemical type	Water-based acrylic blend
Appearance	Milky white frost bubbles
Flash point	Will not burn
NFPA 704 flammability rating	0 (Non-flammable)
Shelf life	3 years, if unopened
Open time	4 hours
Dry time	Once adhesive is dry to touch (10-20 minutes)
Foot traffic allowance	Immediately
Heavy machinery allowance	Immediately
Resistance to moisture	Excellent: 8 lbs/1,000 sq ft or 95% RH/11pH
Underfloor heating systems	Yes
Storage	Do not subject to freezing temperatures

### Characteristics

Provides immediate shear strength after installation allowing instant access to finished floor.

Solvent free, emits no harmful fumes, and contains 0.020 g/ml VOC (Volatile Organic Compounds) in content, according to EPA Test Method 8260B.

Uses non-ozone depleting HFC propellant.

Withstands 8 lbs. of vapor emissions, 95% RH and 11 pH.