



Altro XpressLay™

Tender text

PRODUCT DESCRIPTION

- Manufacturer and product reference:
 - **Altro XpressLay** 2.2 mm thick adhesive-free safety floor by Altro Limited
- Product specification according to EN 13845
- Heterogeneous PVC floor covering with polyester cellulose glass fibre reinforcement and profiled backing
- **o-Phthalate free – plasticisers based on natural resources**
- **Area of use:**
 - General purpose areas
- Surface protection: **Easyclean PUR**
- EN ISO 10874: **Class 34 / 43**
- Slip potential: Pendulum test value (PTV) (minimum) to BS 7976: **≥ 36 (wet)**
- Recycled content: **5%**
- Surface roughness (Rz) (minimum) to BS 1134: **≥ 20 micron**
- Width: **2000 mm**
- Thickness: **2.2 mm**
- Colour: **TBC**
- Guarantee: **10 years**
- Seam welding: **Hot-welding with matching Altro welding rod**
- Adhesive-free
- Altro adhesive-free flooring: **Approved installation tape must be used at perimeter and at joints**
- The Altro quality and environmental management systems are certified according to ISO 9001:2015 and ISO 14001:2015

Property	Standard	Performance
Flooring Type	EN 13845 / EN 13553	Resilient adhesive-free safety flooring
Thickness	EN ISO 24346	2.2 mm
Wear layer thickness	EN ISO 24340	0.8 mm
Roll dimensions	EN ISO 24341	2.0 m x 20.00 m – 40 m ²
Weight	EN ISO 23997	2.6 kg/m ²
Classification for use	EN ISO 10874	34 / 43
Fire performance	EN 13501-1 EN ISO 9239-1 EN ISO 11925-2	Class Bfl-s1 ≥ 8 kW/m ² Pass
Slip resistance	BS 7976 / PTV EN 13845 EN 13893 DIN 51130	≥ 36 ESf ≥ 0.30 / DS R10
Flexibility	EN ISO 24344	Pass
Light fastness	EN ISO 105-B02	≥ 6
Wear resistance	EN 13845	≤ 10% particles lost over 50000 cycles
Castor chair abrasion	EN 425	Pass
Residual indentation	EN ISO 24343	≤ 0.10 mm
Sound insulation	ISO 140-8	Ca. 7 dB
Chemical resistance	EN ISO 26987	Good
Under floor heating	EN 12524	Suitable 27°C at adhesive line
Electrical behaviours	EN 1815	≤ 2 kV Antistatic
VOC Emissions	CDPH 1350 / Floorscore / M1	Approved