

Altro wall systems

Data sheet
Altro Tegulis™

Altro Tegulis tile-effect wall panels offer an alternative to traditional tiles for wet rooms, bathrooms, kitchens, and retail spaces. The custom-etched grout lines offer a hygienic solution eliminating the cleaning and repair issues often associated with tiles. Altro Tegulis is suitable where sheet may come into contact with food.

Description

Extruded semi-rigid PVCu sheet.

| | |
|-----------------------|---------------------------|
| Colour: | Various |
| Surface finish: | Satin |
| Thickness: | 2.5mm |
| Size: | Contact Altro for details |
| Maximum service temp: | 60°C |

Altro Tegulis PVCu extruded sheet is supplied with a protective film on its face which can be left in place until the room is ready for use.

This also helps to protect the surface from dust while other trades are in the area. It is ideal for applications requiring a hygienic easy-to-clean, almost maintenance free wall finish, which conforms to UK and European hygiene requirements.

Fixing

The sheets can be fixed directly to most dry substrates depending on its surface suitability, using one of the following methods:

1. AltroFix™ W139 fully bonded system
2. AltroFix™ W157 fully bonded system

Cutting

Cutting to be carried out using a fine tooth circular saw with TCT cutting blades and pressure guide, fine tooth blade jigsaw, a fine tooth handsaw, a high speed TCT router.

Jointing

1. Half-lap joint - an engineered edge which matches the adjacent sheet and combined with Altro sanitary sealant to form a secure and watertight joint
2. Interlocking joint - the edge profile interlocks with the adjacent sheet giving an almost invisible joint between sheets. This jointing solution is ideal for dry environments

Internal / external corners

Internal corners are normally butt jointed and sealed with Altro sanitary sealant. External corners can be finished with the A953 ShowerKit trim.

Vulnerable external corners are usually over-clad with stainless steel corner protectors.

Cleaning

Regular cleaning using a soft cloth and a suitably diluted mild detergent is all that is normally required. Stubborn marks can be removed with Altro Cleaner A859 (do not use on surfaces based on Altro Whiterock wall designs colours) or nonabrasive domestic type cream bath cleaner.

Do not use abrasive pads or wire wool. Do not clean above 60°C. Cleaning cards are available on request.

Chemical resistance

Resistant to a wide range of chemicals, specific details on request.

Storage & conditioning (on-site)

Sheets should be stored flat, fully supported and left for 24 hours to attain the ambient room temperature prior to installation (min 14°C). Sheets should be stored between 14°C – 27°C and must not be stored outside in direct sunlight as distortion can occur.

Limitations of use

Altro Tegulis has a maximum working temperature of 60°C. For temperatures above this use stainless steel. Stainless steel must be used for all open flame areas (available cut to size) must be extended to min 300 mm past heat source. If a layout showing the position of equipment can be supplied, we will provide specific advice as to the best combination of materials to use.

Typical applications

- bars /cafes / restaurants
- care homes - kitchens and bathrooms
- supermarket counters
- student accommodation – kitchens and bathrooms

Our Technical Services Department is available for advice on 01462 707600.

Technical data

| Property | Standard | Value |
|--|-------------|--|
| Surface finish | | Satin |
| Thickness | | 2.5 mm |
| Size | | Contact Altro for details |
| Weight | | 3300 g/m ² - 3600 g/m ² |
| Density | ISO 1183 | 1.44 g/cm ³ |
| Maximum service temperature | | 60°C |
| Hardness (Shore D) | ISO 868 | 76 |
| Fire resistance | EN 13501-1 | B- s3, d0 |
| Notched Impact resistance | ISO 179/1ea | 9.5 KJ/m ² |
| Impact resistance | ISO 179/1eU | +20°C without breakage 0°C without breakage -20°C without breakage |
| Flexural strength | ISO 178 | 70 MPa |
| Tensile strength | ISO 527 | 52 MPa |
| E-modulus of elasticity | ISO 527 | 2950 MPa |
| Compressive strength | DIN 53421 | 68 N/mm ² |
| Vicat softening point VST/B | ISO 306 | 73°C |
| Expansion coefficient | DIN 53752 | 0.07 mm/mK |
| Heat distortion temperature | ISO 75-2 | 60 °C |
| Water Absorption | ISO 62 | ≤ 0.1% |
| Thermal Conductivity | EN 12524 | 0.17 W/mK |
| “U” value (bonded to 100mm block wall) | DIN 52612 | 1.8 W/m ² °C |
| Moisture Vapour Transmission rate (MVTR) | ASTM E96 | ≤ 0.12g/m ² /24hrs |
| Water vapour resistivity | ASTM E96 | 3.82 x 10 ⁵ GN.S/Kg.m |

For further information or technical advice

tel: 01462 707600

email: enquiries@altro.com or www.altro.com