



Altro Wood™

safety flooring



1000 x 125 mm

Ranch Oak | WSA2021
WR335 / A1M335 / LRV 51



500/500 x 100 mm

Bleached Oak | WSA2001
WR335 / A1M335 / LRV 52



500/500 x 100 mm

Sessile Oak | WSA2027
WR350 / A1M483 / LRV 30



500/500 x 100 mm

Washed Oak | WSA2015
WR347 / A1M347 / LRV 38



500/500 x 100 mm

Farmhouse Oak | WSA2004
WR338 / A1M338 / LRV 38



500/500 x 100 mm

Rustic Oak | WSA2006
WR340 / A1M340 / LRV 37



500/500 x 100 mm

Oak Traditions | WSA2013
WR353 / A1M225 / LRV 25



550/450 x 100 mm

Spring Maple | WSA2018
WR352 / A1M352 / LRV 27



550/450 x 100 mm

Autumn Maple | WSA2005
WR339 / A1M339 / LRV 24



500/500 x 100 mm

Bavarian Oak | WSA2026
WR514 / A1M514 / LRV 21



1000 x 125 mm

Mountain Oak | WSA2022
WR339 / A1M339 / LRV 22



500/500 x 100 mm

Honey Oak | WSA2028
WR352 / A1M352 / LRV 21



550/450 x 100 mm

Slate Oak | WSA2029
WR478 / A1M390 / LRV 26



550/450 x 100 mm

Vintage Cherry | WSA2002
WR336 / A1M239 / LRV 22



550/450 x 100 mm

Urban Cherry | WSA2003
WR337 / A1M337 / LRV 17



550/450 x 100 mm

Antique Walnut | WSA2007
WR341 / A1M160 / LRV 15



1000 x 125 mm

Worn Oak | WSA2023
WR322 / A1M239 / LRV 19



500/500 x 100 mm

Manor Oak | WSA2016
WR348 / A1M348 / LRV 7




















Dimensions indicate plank size within roll design.



Typical applications

Hospital / care homes: corridors, living areas. Patient rooms. Retail. Kindergartens, schools, universities: general circulation areas, corridors.

Technical information

| | | | |
|---|------------------------------------|--|--|
|  | Fire behaviour tested in acc. with | EN ISO 9239-1 EN ISO 11925-2 EN 13501-1 | ≥ 8 kW/m ² Pass B _{f1} -s1 |
| | Classified in acc. with | | |
|  | Slip resistance | EN 13893 PTV DIN 51130 / BGR 181 EN 13845 Annex C | ≥ 0.30 / DS ≥ 36 R10 ESf |
|  | Sound insulation | EN ISO 10140 | ca. 4 dB |
|  | Flooring type | EN 13845 | Safety flooring |
|  | Thickness | EN ISO 24346 | 2 mm |
|  | Wear layer thickness | EN ISO 24340 | 0.7 mm |
|  | Roll dimensions | EN ISO 24341 | 2 m x 20 m = 40 m ² |
|  | Weight | EN ISO 23997 | 2.66 kg/m ² |
|  | Residual indentation | EN ISO 24343-1 | ≤ 0.10 mm |
|  | Classification for use | EN ISO 10874 | 34, 43 |
|  | Flexibility | EN ISO 24344 | Pass |
|  | Dimensional stability | EN ISO 23999 | ≤ 0.4 % |
|  | Light fastness | EN ISO 105-BO2 | ≥ 6 |
|  | Castor chair abrasion | EN 425 | Yes, type W |
|  | Wear resistance | EN 660-2 | Group T |
|  | Chemical resistance | EN ISO 26987 | Good |
|  | Underfloor heating | EN 12524 | Suitable |
|  | Electrical behaviours | EN 1815 | ≤ 2 kV, antistatic |
|  | VOC emissions | CDPH 1350 / Floorscore Indoor Air Comfort Gold | Approved Approved |



Altro Limited a company certified by SGS to ISO 9001 and ISO 14001.



13 | debolon dessauer bodenbeläge GmbH & Co. KG,
Ebertallee 209, 06846 Dessau-Roßlau | DIN EN 13845 |
DoP-No. Altro Wood Safety-RN-A025 | Reaction to fire: Bfl s1 |
Slip resistance: DS | Formaldehyde: E1 |
Electrical behaviour: < 2 kV | EN 14041:2004/AC:2006 | 1658 |
Resilient floor covering to be used within a building



*Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).



Sustainability



*A+ BRE generic green guide rating for resilient flooring, full details available at www.thegreenguide.org.uk

Installation and maintenance

Please refer to Altro installation and maintenance instructions. Failure to follow these instructions can affect product performance. Technical information on installation and staining can be found at www.altro.com

 Altro, Designed for possibilities. Made for people. Altro Wood and Altro Easyclean technology are trademarks of Altro Limited.

United Kingdom

+44 (0) 1462 707 700

enquiries@altro.com

Australia

+61 3 9764 5666

info@asf.com.au

Subject to alteration.