
















Altro Transflor Wood™ Patent No. GB 2 462 167

Flooring type Tipo de pavimento Belagsart		EN 13845 ASTM F1303	Safety flooring Suelo de seguridad antideslizante Rutschfester Bodenbelag
Thickness Espesor total Gesamtdicke		EN ISO 24346	2.2 mm / 0.088"
Wear layer Capa de uso Nutzschicht		EN ISO 24340	0.7 mm / 0.027"
Roll dimensions Dimensiones del rollo Rollenformat		EN ISO 24341	2m x 20m = 40m ² 6'7" x 65'7"
Weight Peso Flächengewicht		EN ISO 23977	2.68 kg/m ² 4.93 lb/sy
Fire Performance Reacción al fuego Brandverhalten		ECE R-118 FMVSS 302 / CMVSS 302	Pass / Bestanden / Conforme Pass / Bestanden / Conforme
Slip resistance Resistencia al deslizamiento Rutschsicherheit		BAM EN 13893 EN 13845 ASTM D2047 PTV DIN 51130	Dry - very slip resistant muy antideslizante stark rutschhemmend Wet - slip resistant antideslizante rutschhemmend DS ESf ≥0.6 ≥ 36 R10
Flexibility Flexibilidad Flexibilität		EN 435 ASTM F1303	Pass Conforme Bestanden
Light fastness Resistencia a la luz Farbbeständigkeit/Lichtechtheit		EN ISO 105-B02	≥6
Wear resistance Abrasión Verschleißgruppe		EN13845	≤10% particles lost over 50000 cycles ≤10% de las partículas perdidas en 50.000 ciclos ≤10% Partikel werden über 50,000 Umdrehungen verloren
Castor Chair Abrasion Huellas de ruedas de sillas Stuhlleneignung		EN 425	Pass Conforme Bestanden
Indentation Punzonamiento Resteindruck		EN ISO 24343-1 ASTM F970	≤ 0.10 mm
Chemical resistance Resistencia a los productos químicos Chemikalieneinwirkung		EN 423	Good Buena Gut
Electrical behaviours Características eléctricas Elektrostatisches Verhalten		EN 1815	≤ 2kV Antistatic ≤ 2kV Antiestáticas ≤ 2kV Antistatisch
VOC emissions Emisiones de VOC VOC emissionen		IAC Gold	Pass Conforme Geignet